

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
25 September 2003 (25.09.2003)

PCT

(10) International Publication Number
WO 03/078487 A1

(51) International Patent Classification⁷: **C08F 255/00**,
287/00, 8/46

(IT). MASI, Francesco [IT/IT]; Via Galvani, 7/0, I-26866
Sant'Angelo Lodigiano-Lodi (IT).

(21) International Application Number: PCT/EP03/02636

(74) Agents: **DE GREGORI, Antonella et al.**; Barzano' &
Zanardo Milano S.P.A, Via Borgonuovo 10, I-20121 Milan
(IT).

(22) International Filing Date: 12 March 2003 (12.03.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
MI2002A000583 20 March 2002 (20.03.2002) IT

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD,
SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.

(71) Applicant (*for all designated States except US*):
POLIMERI EUROPA S.P.A. [IT/IT]; Via E. Fermi
4, I-72100 Brindisi (IT).

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicants (*for US only*): **CASABURO, Orsola** (heiress
of the deceased inventor) [IT/IT]; Via Europa , 20, I-20097
San Donato Milanese-Milan (IT). **BIGGI, Lisa** (heiress of
the deceased inventor) [IT/IT]; Via Europa , 20, I-20097
San Donato Milanese-Milan (IT). **BIGGI, Silvia** (heiress
of the deceased inventor) [IT/IT]; Via Europa , 20, I-20097
San Donato Milanese-Milan (IT).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

(72) Inventor: **BIGGI, Aroldo** (deceased).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **TANAGLIA,**
Tiziano [IT/IT]; Via della Battaglia 2, I- 40141 Bologna

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: **PROCESS FOR THE FUNCTIONALIZATION OF POLYOLEFINS**

(57) Abstract: Process for the preparation of functionalized polyolefins, which comprises treatment under shear conditions of said polyolefins with an unsaturated monomer containing polar groups in the presence of at least one hydroperoxide as radicalic initiator. The process allows the grafting of unsaturated monomers without the formation of cross-linked polymeric material and without modifying the molecular weight distribution.

WO 03/078487 A1

5

PROCESS FOR THE FUNCTIONALIZATION OF POLYOLEFINS

The present invention relates to a process for the functionalization of polyolefins by treatment, under shear
10 conditions, of said polyolefins with an unsaturated monomer containing polar groups in the presence of at least one hydroperoxide as radicalic initiator.

Polyolefins are non-polar products which have a poor affinity with traditional materials such as for example,
15 glass and metals in general, and are incompatible with polar synthetic polymers such as polyesters and polyamides. Furthermore, polyolefins have a limited adhesion strength to these materials.

The preparation of composite or laminated materials
20 starting from polyolefins as such and from the above traditional materials, consequently creates considerable difficulties.

These difficulties have given rise, in relatively recent times, to intense research activities aimed at obtaining
25 polyolefins with improved surface properties.

Reactions relating to the functionalization of polyolefins by the grafting of polar monomers using radicalic reactions promoted by peroxides, have been described in literature.

5 For example patent U.S. 4,147,746 describes the modification reaction of polyethylene with derivatives of maleic, itaconic and citraconic acid in the presence of peroxides.

10 When the modification reaction of polyolefins, however, must ensure that the physico-chemical and rheological characteristics of the starting polyolefin are kept as unvaried as possible, the use of peroxides as radicalic initiators can be unsatisfactory.

15 It is known in fact that peroxides favour the cross-linking of polyolefins, in particular EPDM, in competition with the grafting reaction and produce undesired increases in the molecular weight and a broadening of the molecular weight distribution.

20 Reactions relating to the functionalization of polyolefins in which hydroperoxide is indicated among the possible initiators, have been described in literature (JP-55016022, GB-1168959).

25 Under the conditions in which the functionalization takes place in the above patents, however, low shear and a temperature higher than the decomposition value, the hydro-

peroxide behaves in exactly the same way as any radicalic initiator.

It has now been found that by using hydroperoxides under shear conditions in the grafting reaction of polyolefins with an unsaturated monomer, it is possible to obtain functionalized polyolefins effectively reducing the cross-linking phenomena of the substrate. There are consequently no uncontrolled increases in the molecular weight or the formation of microgels and branchings which can influence the processability of the end-product.

In accordance with this, the present invention relates to a process for the functionalization of polyolefins which comprises the treatment of polyolefins under shear conditions with an unsaturated monomer containing polar groups in the presence of at least one hydroperoxide as radicalic initiator.

The polyolefins can be used in the process of the present invention are selected from:

- copolymers of ethylene with α -olefins;
- 20 - copolymers of propylene with α -olefins;
- ethylene/propylene copolymers (EPM) with a molar propylene content ranging from 16% to 50%, preferably from 20% to 45%, and a number molecular weight (Mw) ranging from 10,000 to 200,000;
- 25 - ethylene/propylene/non-conjugated diolefin (EPDM) ter-

polymers.

Typical examples of non-conjugated diolefins are 1,4-hexadiene, 1,5-heptadiene, 1,6-octadiene, 1,4-cyclohexadiene, 5-methylene-2-norbornene, 5-ethylidene-2-norbornene. These EPDM usually have a molar ethylene content ranging from 40 to 85%, preferably from 40 to 70%; from 15 to 70%, preferably from 30 to 60% molar, of propylene; from 0.5 to 20% molar, preferably from 1 to 15%, even more preferably from 2 to 10% molar of non-conjugated diene.

10 The molecular weights M_w of the EPDM are within the range of 75,000 to 450,000, preferably from 100,000 to 180,000 and the non-conjugated diene is preferably 5-ethylidene-2-norbornene;

- thermoplastic elastomers deriving from butadiene and/or
15 isoprene and styrene block copolymers, hydrogenated and non-hydrogenated.

The polyolefins which can be used for the purposes of the present invention can be prepared according to any of the methods known in the art.

20 With respect to the hydroperoxide (or mixture of hydroperoxides) which can be used for the purposes of the present invention, any hydroperoxide can be used, which, at the process temperature, does not undergo a significant decomposition. In other terms, the hydroperoxide preferably
25 has a half-life which is not shorter than the process time,

even more preferably not less than 10 times the process time.

Typical examples of hydroperoxides are cumene hydroperoxide, hydrogen peroxide, t-butyl hydroperoxide, 2,5-
5 dihydroperoxy-2,5-dimethyl hexane.

Polar unsaturated monomers which can be used in the process of the present invention are selected from derivatives of unsaturated carboxylic acids such as esters, amides, acids, metallic salts of acrylic acid, fumaric acid,
10 itaconic acid, citraconic acid and maleic acid, maleic anhydride, esters of vinyl alcohol, vinyl silane derivatives, vinyl imidazole derivatives, vinyl oxazole derivatives, vinyl pyridine derivatives.

Maleic anhydride and its derivatives are preferably
15 used.

The hydroperoxide is added to the polymeric material as such or dissolved in a suitable solvent.

The concentration of hydroperoxide with respect to the polyolefins ranges from 0.1 to 20% by weight, preferably
20 from 0.2 to 10% by weight, even more preferably from 0.5% to 5% by weight.

The quantity of monomer used in the present invention generally ranges from 0.1 to 10, preferably from 0.4 to 1.5% with respect to the polyolefins.

25 The process of the present invention is carried out

under high shear conditions, usually higher than 100 sec^{-1} , preferably higher than 1000 sec^{-1} .

The process is carried out at a temperature ranging from 80 to 250°C , preferably from 140 to 200°C for a time
5 ranging from 1 to 1800 seconds, preferably from 30 to 600 seconds.

The above process can be effected in a reactor suitable for the purpose such as, for example, a batch mixer or an extruder.

10 The process of the present invention is preferably carried out in an extruder, even more preferably in a twin-screw extruder.

The process of the present invention is effected without the introduction of oxygen and can be carried out either batchwise or in continuous. When operating batchwise,
15 the single components are added in a suitable reactor together or in reasonable portions, in the presence or absence of a solvent, preferably without a solvent.

When operating in continuous, the reagents are added
20 continuously, at a suitable feeding rate, to a reactor (or a reactor zone) thermostat-regulated at the desired temperature.

At the end of the above process, if necessary for the subsequent application, antioxidants, light and heat stabilizers, nucleating agents, organic and inorganic dyes or
25

other additives selected from those known in the art, can be added.

The polyolefins modified according to the process of the present invention can be used in various fields, particularly in the production of coating materials and laminates.

The following examples are provided for a better understanding of the present invention.

EXAMPLES

10 All the examples were carried out using the same polymer, a commercial EPDM ENICHEM DUTRAL^R ter 4033 having 25% by weight of propylene, 4.9% by weight of ethylidene-norbornene (ENB) - MFI (L) = 2.4 g/10 minutes.

The t-butyl hydroperoxide (TBHP) used was supplied by 15 Akzo Nobel at 70% in aqueous solution (trade-name Trigonox^R AW70).

The dicumyl peroxide (DCP) was supplied by Elf-Atochem carried at 40% on EPR (trade-name Peroximon^R DC40).

Diethyl maleate (DEM) was used as modifying monomer. 20 The chemical modification was determined by means of IR analysis of the product washed in acetone. The presence and intensity of the band at about 1740 cm⁻¹ is evidence of grafting.

An internal quantitative method based on the height of 25 the band was used to avoid interaction with other bands.

The value obtained, calculated on the basis of calibrations on ester groups different from the bound DEM, does not exactly correspond to the concentration of grafted DEM, but must be used as a comparison.

5 EXAMPLE 1

A 70 cc mixing chamber is charged with 40 g of EPDM polymer DUTRAL^R Ter 4033, 1% of t-butyl hydroperoxide and 3.3% of diethyl maleate (DEM), thermostat-regulated at 105°C (external) and kept under mixing at 50 revs/minute. A
10 temperature of 130°C is reached at equilibrium.

The mixture is left to plasticize for 60 seconds, and the rate of the rotors is then suddenly increased to 200 revs/minute; the temperature rises (maximum temperature of the molten product 190°C) and the torque pair measured with
15 the instrument is slowly lowered.

After 2 minutes of mastication, the experiment is interrupted and the product recovered.

The results of the analyses are indicated in Table 1.

EXAMPLE 2 (comparative)

20 The mixing chamber of Example 1 is charged with 40 grams of polymer DUTRAL Ter 4033 and 3.3% of DEM, thermostat-regulated at 105°C (external) and kept under mixing at 50 revs/minute. A temperature of 130°C is reached at equilibrium.

25 The mixture is left to plasticize for 60 seconds, and

the rate of the rotors is then suddenly increased to 200 revs/minute; the temperature rises (maximum temperature of the molten product 180°C) and the torque pair measured with the instrument is slowly lowered.

5 After 2 minutes of mastication, the experiment is interrupted and the product recovered.

The results of the analyses are indicated in Table 1.

EXAMPLE 3 (comparative)

The mixing chamber of Example 1 is charged with 40
10 grams of polymer DUTRAL Ter 4033, 0.3% of dicumyl peroxide (DCP) and 3.3% of DEM, thermostat-regulated at 105°C (external) and kept under mixing at 50 revs/minute. A temperature of 130°C is reached at equilibrium.

The mixture is left to plasticize for 60 seconds, and
15 the rate of the rotors is then suddenly increased to 200 revs/minute; the temperature rises (maximum temperature of the molten product 195°C) and the torque pair measured with the instrument is slowly lowered.

After 2 minutes of mastication, the experiment is in-
20 terrupted and the product recovered.

The results of the analyses are indicated in Table 1.

EXAMPLE 4 (comparative)

The mixing chamber of Example 1 is charged with 40
grams of polymer DUTRAL Ter 4033, 1% of t-butyl hydroperox-
25 ide, at a temperature of about 160°C (external) and kept

under mixing at 60 revs/minute. The temperature is then gradually increased to 220°C. After 4 minutes, the product is recovered.

The results of the analyses are indicated in Table 1.

5

TABLE 1

10

Example	Solubility in ODCB	Arbitrary grafting unit (IR)
1	complete	0.70
2	complete	0.03
3	insoluble	n.d. (*)
4	40%	n.d.

(*) not determined.

From Table 1 it can be seen that the combined use of hydroperoxide and shear conditions (Example 1) produces unexpected advantageous effects with respect to the prior art.

It is possible in fact to use polymers critical for peroxide treatment with hydroperoxide, without observing cross-linking and obtaining grafting reactions with respect to polar monomers such as DEM.

25

CLAIMS

1. A process for the functionalization of polyolefins which comprises the treatment under shear conditions of polyolefins with an unsaturated monomer containing polar groups in the presence of at least one hydroperoxide as radicalic initiator.
2. The process according to claim 1, wherein the polyolefins are selected from saturated or unsaturated polyolefinic copolymers and relative mixtures.
3. The process according to claim 2, wherein the polyolefins are selected from:
 - copolymers of ethylene with α -olefins;
 - copolymers of propylene with α -olefins;
 - ethylene/propylene copolymers (EPM) with a molar propylene content ranging from 16% to 50%, and an Mw ranging from 10,000 to 200,000;
 - ethylene/propylene/non-conjugated diolefin (EPDM) terpolymers with a molar ethylene content ranging from 40 to 85%, from 15 to 70% of propylene and 2 to 10% molar of non-conjugated diene, the molecular weights Mw of the EPDM being within the range of 75,000 to 450,000;
 - thermoplastic elastomers deriving from butadiene and/or isoprene and styrene block copolymers, hydrogenated and non-hydrogenated.

4. The process according to claim 3, wherein the ethylene/propylene (EPM) copolymers have a molar propylene content ranging from 20% to 45%.
5. The process according to claim 3, wherein the ethylene/propylene/non-conjugated diolefin (EPDM) terpolymers have a molar ethylene content ranging from 40 to 70%, from 30 to 60% of propylene and from 0.5 to 20% of non-conjugated diene.
6. The process according to claim 5, wherein the ethylene/propylene/non-conjugated diolefin (EPDM) terpolymers have a molar content of non-conjugated diene ranging from 1 to 15% molar.
7. The process according to claim 6, wherein the ethylene/propylene/non-conjugated diolefin (EPDM) terpolymers have a molar content of non-conjugated diene ranging from 2 to 10% molar.
8. The process according to claim 5, wherein the ethylene/propylene/non-conjugated diolefin (EPDM) terpolymers have a molecular weight Mw ranging from 100,000 to 180,000.
9. The process according to claim 3, wherein the non-conjugated diolefins are selected from 1,4-hexadiene, 1,5-heptadiene, 1,6-octadiene, 1,4-cyclohexadiene, 5-methylene-2-norbornene, 5-ethylidene-2-norbornene.
10. The process according to claim 9, wherein the non-

conjugated diolefin is 5-ethylidene-2-norbornene.

11. The process according to claim 1, wherein the hydroperoxide is selected from cumene hydroperoxide, hydrogen peroxide, t-butyl hydroperoxide, 2,5-dihydroperoxy-2,5-dimethyl hexane.
12. The process according to claim 1, wherein the concentration of hydroperoxide with respect to the polyolefins ranges from 0.1 to 20% by weight.
13. The process according to claim 12, wherein the concentration of hydroperoxide with respect to the polyolefins ranges from 0.2 to 10% by weight.
14. The process according to claim 13, wherein the concentration of hydroperoxide with respect to the polyolefins ranges from 0.5% to 5% by weight.
15. The process according to claim 1, wherein the polar unsaturated monomers are selected from unsaturated carboxylic acids such as esters, amides, acids, metallic salts of acrylic acid, fumaric acid, itaconic acid, citraconic acid and maleic acid, maleic anhydride, esters of vinyl alcohol, vinyl silane derivatives, vinyl imidazole derivatives, vinyl oxazole derivatives, vinyl pyridine derivatives.
16. The process according to claim 15, wherein the polar unsaturated monomers are selected from maleic anhydride and its derivatives.

17. The process according to claim 1, wherein the quantity of polar unsaturated monomers ranges from 0.1 to 10% with respect to the polyolefins.
18. The process according to claim 17, wherein the quantity of polar unsaturated monomers ranges from 0.4 to 1.5% with respect to the polyolefins.
19. The process according to claim 1, carried out at a temperature ranging from 80 to 250°C, for a time ranging from 1 to 1800 seconds.
20. The process according to claim 19, wherein the temperature ranges from 140 to 200°C and the time ranges from 30 to 600 seconds.

15

20

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 03/02636

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F255/00 C08F287/00 C08F8/46

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR 1 466 197 A (GRACE W R & CO) 13 January 1967 (1967-01-13) example 1	1,2, 11-16, 19,20
X	GB 1 168 959 A (ALLIED CHEMICAL CORPORATION) 29 October 1969 (1969-10-29) examples	1,2, 11-15, 19,20
X	FR 1 494 634 A (GOODRICH CO B F) 8 September 1967 (1967-09-08) examples	1-3,5-7, 19,20
X	US 6 107 405 A (SCHERTZ DAVID MICHAEL ET AL) 22 August 2000 (2000-08-22) claims 1,6,7	1,2
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *&* document member of the same patent family

Date of the actual completion of the international search

9 July 2003

Date of mailing of the international search report

31/07/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Meulemans, R

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 03/02636

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 166 607 A (ALBERTO BONVICINI ET AL) 19 January 1965 (1965-01-19) example 7	1
X	GB 1 217 231 A (ASAHI KASEI KOGYO KABUSHIKI KAISHA) 31 December 1970 (1970-12-31) examples 4,5,8,9	1,2, 11-14, 19,20
X	EP 0 392 783 A (MINNESOTA MINING & MFG) 17 October 1990 (1990-10-17) examples	1,2, 11-14
X	WO 98 25979 A (KIMBERLY CLARK CO) 18 June 1998 (1998-06-18) claims 1-3	1,2,15, 17

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 03/02636

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
FR 1466197	A	13-01-1967	NONE	
GB 1168959	A	29-10-1969	DE 1795027 A1 FR 1575325 A	20-01-1972 09-06-1969
FR 1494634	A	08-09-1967	DE 1595768 A1 NL 6613665 A	30-04-1970 30-03-1967
US 6107405	A	22-08-2000	AU 4977897 A WO 9817702 A1 ZA 9709143 A	15-05-1998 30-04-1998 11-05-1998
US 3166607	A	19-01-1965	BE 564910 A FR 1201501 A GB 875758 A NL 109545 C	30-12-1959 23-08-1961
GB 1217231	A	31-12-1970	DE 1720256 A1 FR 1564548 A	13-04-1972 25-04-1969
EP 0392783	A	17-10-1990	US 5013795 A AU 617047 B2 AU 5294090 A CA 2014156 A1 DE 69020039 D1 DE 69020039 T2 DK 392783 T3 EP 0392783 A2 ES 2074122 T3 HK 1006844 A1 JP 2960100 B2 JP 3054211 A US 5262484 A	07-05-1991 14-11-1991 11-10-1990 10-10-1990 20-07-1995 15-02-1996 30-10-1995 17-10-1990 01-09-1995 19-03-1999 06-10-1999 08-03-1991 16-11-1993
WO 9825979	A	18-06-1998	AU 732005 B2 AU 5897198 A EP 0948550 A1 WO 9825979 A1	12-04-2001 03-07-1998 13-10-1999 18-06-1998